



1602PP Prepolymer

Product Description

1602PP is an MDI based polyurethane prepolymer which may be used as the basis for a range of moisture curing polyurethane coating systems.

One of the applications of **1602PP** is in the manufacture of solvent based moisture curing polyurethane floor coating designed to provide a long lasting economical floor sealer.

Typical Applications

Floor coating systems based on **1602PP** can be used on most surfaces including concrete, cement, asbestos, granolithic floors, plywood and many others.



Method of Use

1602PP is supplied at 60 - 65% solids. **1602PP** may be diluted with a suitable solvent (e.g. Xylene) to 30% solids to make a good moisture curing concrete sealer. The same prepolymer when diluted to 45% solids gives a good clear hardwearing floor coating. At this level of dilution the system may be filled or pigments added to give a wide variety of colours and finishes.



Isothane Limited, Newhouse Road
Huncoat Business Park, Accrington
Lancashire BB5 6NT
Telephone: 01254 872555
Facsimile: 01254 871522
Order Fax Line: 01254 398295
Email: info@isothane.com
Website: www.isothane.com
Registration No: 2975728



Certificate No. FM 21549



INVESTOR IN PEOPLE



Certificate No. EMS 68443

Surface Preparation

Coatings based on **1602PP** should be applied to properly dry surfaces at an ambient temperature of between 5° C and 45°C. Surfaces should be sound and free of loose and flaking material such as dirt, dust, laitance, etc. and should be free from grease, release-agents, silicon or similar treatments, efflorescence and the like. All high spots including builders' debris and detritus should be removed. Any damaged areas can be made good with a suitable repair material. The removal of surface contamination may involve a variety of cleaning processes including acid etching, grit blasting, detergent washing etc. It is essential that these processes are carried out correctly in accordance with manufacturers instructions. The sub-floor should also be provided with a damp-proof membrane in accordance with code of practice 102:1972.

Application

1602PP and derivatives should only be applied to correctly prepared DRY surfaces. It can be applied by brush or roller at a coverage rate of up to 8m² per kilo, allowing 2 - 4 hours between coats, depending upon the ambient temperature and relative humidity. The coverage rate is dependent on the porosity of the substrate and is intended only as a guide. One coat is usually satisfactory for sealing applications but two coats are required for optimum appearance and durability.

Packaging

- **1602PP** is available in 20L American pails.

Storage, Handling and Personal Protection

The recommendations in our Safety Data Sheet for this product must be followed at all times. More general information is included in our publication "A Guide to the Safe Handling of Polyurethane Chemicals".

Technical Data

NCO Content	8.5%
Drying	2 - 4 hrs dependant on temp and relative humidity
Shelf Life	6 months (unopened)
Chemical Resistance	Excellent
SG	1.06
Solids	60 - 65%
Flashpoint	51°C
Viscosity	400 - 500 centipoise
Cleaning Equipment	Xylene or Ethylglycolacetate
Coverage	Up to 8m ² / litre dependent on surface
Storage	Out of direct sunlight

This information is of a general nature and is supplied without recommendation or guarantee. It does not make claim to be free from patent infringement. Properties shown are typical and do not imply specification tolerances. Liability for loss or damage through use cannot be accepted except for death or injury caused by negligence on the part of Isothane Ltd. Whilst these specifications are based on expert knowledge, practical experience and laboratory testing, successful application depends upon the nature and conditions in which the products are applied. Users must, by comprehensive testing, ensure suitability of product for own use. Without control or supervision of the preparation for and application of Isothane products, general guarantees cannot be offered.



Isothane Limited, Newhouse Road
Huncoat Business Park, Accrington
Lancashire BB5 6NT
Telephone: 01254 872555
Facsimile: 01254 871522
Order Fax Line: 01254 398295
Email: info@isothane.com
Website: www.isothane.com
Registration No: 2975728



Certificate No. FM 21549



INVESTOR IN PEOPLE



Certificate No. EMS 68443

