

## REPROCELL 300

### The Alternative to Timber

#### Product Description

**REPROCELL 300** is a dual component, MDI based system which when dispensed through suitable machinery will produce rigid polyurethane foam with typical core density in the range of 300 – 450 kg / m<sup>3</sup>. Reprocell foam systems are free from CFC's or HCFC's and comply with present and forthcoming environmental requirements of Kyoto Protocol.

#### Uses and Applications

**REPROCELL 300** has been designed to produce high density foam which can be moulded to simulate wood for a variety of applications. The cured foam has a tough skin and will accommodate screws and nails, and can be stained using the recognised wood stains, paints or varnishes.

In external applications such as porch furniture, the foam needs to be protected against ultra violet degradation by painting.

**REPROCELL** combines low weight with long-term stability and extremely low water absorption characteristics. It does not decay or rot and is not susceptible to attack by termites or other wood boring insects. Isothane technical personnel are available to advise on specialist processes and surface treatments as required.

#### Equipment

**REPROCELL** systems can be processed through all standard foam dispense equipment. Refer to Isothane technical staff for a specific recommendation. The machine should be capable of maintaining the mix ratio at  $\pm 2\%$  accuracy and controlling the component temperatures at 25 - 45°C (variable).



Isothane Limited, Newhouse Road  
Huncoat Business Park, Accrington  
Lancashire BB5 6NT  
Telephone: 01254 872555  
Facsimile: 01254 871522  
Order Fax Line: 01254 398295  
Email: info@isothane.com  
Website: www.isothane.com  
Registration No: 2975728



Certificate No. FM 21549



INVESTOR IN PEOPLE



Certificate No. EMS 68443



## REPROCELL 300

### Foam Moulding System

#### Component Description

**REPROCELL RESINS** are fully formulated liquid mixtures. They should be stored in sealed tanks or drums and ideally should be heated to  $20 \pm 5^\circ\text{C}$  before use.

**REPROCELL ISO** is a liquid mixture containing crude diphenylmethanediisocyanate. It should be stored in sealed tanks or drums and ideally should be heated to  $20 \pm 5^\circ\text{C}$  before use.

Stored under the above conditions the system has a shelf life of 6 months. See below for component properties.

Laboratory test results ( typical ):-

Cream time	40	seconds
Rise time	120	seconds
Free rise density	300	kg/m <sup>3</sup>

#### Typical Properties

	<u>Reprocell Resin</u>	<u>Reprocell ISO</u>
Appearance	Resinous liquid	Dark brown liquid
Viscosity	1000 - 2000 cps @ 20°C	150 - 270 cps @ 20°C
Specific Gravity	1.05 - 1.10 @ 20°C	1.24 ± 0.02
Mixing Ratio (by wt)	47 parts Resin : 53 parts ISO	
Process	Moulding	


<u>Typical Properties of Foam Core</u>	<u>Value</u>	<u>Test Method</u>
Core Density	300 kg / m <sup>3</sup>	BS 4370
Compressive Strength – Parallel to rise	7000 Kpa	BS 4370
Shear Tensile Strength – Perpendicular to rise	7500 Kpa	BS 4730
Closed Cell Content	90% min	BS 4730
Thermal Conductivity – 20°C Mean	~0.04 W / mK	ASTM D2856
Water Absorption	0.05 kg / m <sup>2</sup>	
Dimensional Stabilities		
24 HRS @ 100°C	-0.03    -0.05%	
24 HRS @ -15°C	-0.01    -0.02%	
24 HRS @ 70°C	+ 0.50    +0.55%	

This information is of a general nature and is supplied without recommendation or guarantee. It does not make claim to be free from patent infringement. Properties shown are typical and do not imply specification tolerances. Liability for loss or damage through use cannot be accepted except for death or injury caused by negligence on the part of Isothane Ltd. Whilst these specifications are based on expert knowledge, practical experience and laboratory testing, successful application depends upon the nature and conditions in which the products are applied. Users must, by comprehensive testing, ensure suitability of product for own use. Without control or supervision of the preparation for and application of Isothane products, general guarantees cannot be offered.

**REPROCELL 300**  
**Storage, Handling and Personal Protection**

The recommendations in our Safety Data Sheet for this product must be followed at all times. More general information is included in our publication “A Guide to the Safe Handling of Polyurethane Chemicals” and in the following Technical Data Sheets which are available on request: -

- Fire safety when Storing, Handling and Installing Polyurethane Foam.
- Decontamination of Isocyanates using Isothane Decontaminant.



This information is of a general nature and is supplied without recommendation or guarantee. It does not make claim to be free from patent infringement. Properties shown are typical and do not imply specification tolerances. Liability for loss or damage through use cannot be accepted except for death or injury caused by negligence on the part of Isothane Ltd. Whilst these specifications are based on expert knowledge, practical experience and laboratory testing, successful application depends upon the nature and conditions in which the products are applied. Users must, by comprehensive testing, ensure suitability of product for own use. Without control or supervision of the preparation for and application of Isothane products, general guarantees cannot be offered.



Isothane Limited, Newhouse Road  
Huncoat Business Park, Accrington  
Lancashire BB5 6NT  
Telephone: 01254 872555  
Facsimile: 01254 871522  
Order Fax Line: 01254 398295  
Email: info@isothane.com  
Website: www.isothane.com  
Registration No: 2975728



Certificate No. FM 21549



INVESTOR IN PEOPLE



Certificate No. EMS 68443